

EFENDİ FABRIC INDOOR & OUTDOOR TEST RESULT

Desen Adı <i>Quality Name</i>	İçerik <i>Composition</i>	Gramaj (g/m ²) <i>Weight (g/m²)</i>	Kopma Mukavemeti (Warp/Weft) <i>Tensile Strength (Warp/Weft)</i>	Yırtılma Mukavemeti (Warp/Weft) <i>Tear Strength (Warp/Weft)</i>	Martindale <i>Martindale Abrasion</i>	Boncuklanma <i>Pilling</i>	Kumaş Eni (cm) <i>Fabric Width (cm)</i>
AQUA 1XX	%92 OLF %8 PES	540	527.6 / 560.4	3.45 / 3.26	30.000	4-5	139-142
AQUA 2XX	%100 OLF	460	544.7 / 501.1	3.18 / 3.07	25.000	4-5	139-142
AQUA 3XX	%97 OLF %3 PES	640	389.6 / 515.2	2.46 / 3.43	35.000	4-5	139-142
AQUA 4XX	%32 OLF %68 PES	460	1470.1 / 1038.1	112.0 / 231.4	40.000	4-5	139-142
AQUA PLN 1	%59 OLF %41 PES	410	119.5 / 331.0	2.14 / 2.69	20.000	4-5	139-142
AQUA PLN 2	%32 OLF %68 PES	380	1586.3 / 1024.3	68.1 / 70.2	50.000	4-5	139-142

* All tests were performed according to international standards. Values represent average laboratory results.